

Appl. No. 10/714,021  
Reply to Office Action of May 29, 2007  
Amendment dated: October 29, 2007

RECEIVED  
CENTRAL FAX CENTER

OCT 29 2007

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A magnetic recording medium comprising:  
  
a non-magnetic supporter;  
  
a first magnetic layer formed above said non-magnetic supporter and formed from a magnetic paint having a first ferromagnetic material; and  
  
a second magnetic layer formed above said first magnetic layer and formed from a magnetic paint having a second ferromagnetic material, wherein the first magnetic layer and the second magnetic layer include polyester polyol having an alicyclic framework and a polyurethane resin composed of diisocyanate and wherein a concentration of a urethane group in the polyurethane resin ranges from 0.5 mmol/g to 3.0 mmol/g, the first magnetic layer having a thickness approximately five times greater than a thickness of the second magnetic layer and wherein a combined thickness of said first and second magnetic layers is approximately 3.0  $\mu\text{m}$  and further wherein at least one of the first and second magnetic layers includes alkali metal sulfonate incorporated into the resin at concentration of .001 mmol per gram to 1.0 mmol per gram.
2. (Previously Presented) The magnetic recording medium according to claim 1, wherein the magnetic paints are formed from a powder and wherein a content of the polyurethane resin has a mixing ratio relative to the weight of magnetic powder, said mixing ratio being the same in the first magnetic layer and the second magnetic layer.

Appl. No. 10/714,021  
Reply to Office Action of May 29, 2007  
Amendment dated: October 29, 2007

3. (Currently Amended) The magnetic recording medium according to claim 1, wherein tertiary amine or ~~metal sulfonate~~ is included in the polyurethane resin.
4. (Currently Amended) The magnetic recording medium according to claim 2, wherein tertiary amine or ~~metal sulfonate~~ is included in the polyurethane resin.
5. (Withdrawn) A magnetic recording medium having magnetic recording layers of multiple layers in which a first magnetic layer and a second magnetic layer are applied in order on a non-magnetic supporter, wherein the first magnetic layer includes carbon black having an average particle size of 80 nm or smaller and an abrasive having Mohs scale of 6 or higher, and the second magnetic layer includes MT carbon black having an average particle size of 200 nm to 400 nm and an abrasive having Mohs scale of 6 or higher.
6. (Withdrawn) The magnetic recording medium according to claim 5, wherein assuming that the thickness of the first magnetic layer is  $t_1$ , the thickness of the second magnetic layer is  $t_2$  and the particle size of the abrasive is  $r$ , when  $t_1$  is not larger than  $t_2$ , the following relation is satisfied.  $0.5 \times t_2 \leq r \leq t_2$ .
7. (Withdrawn) The magnetic recording medium according to claim 6, wherein the thickness  $t_2$  of the second magnetic layer is not smaller than  $0.2 \mu\text{m}$  and not larger than  $1.0 \mu\text{m}$ .
8. (Previously Presented) The magnetic recording medium of claim 1, wherein the magnetic paints used to form said first magnetic layer and said second magnetic layer are formed from magnetic powders and wherein the

Appln. No. 10/714,021  
Reply to Office Action of May 29, 2007  
Amendment dated: October 29, 2007

quantity of polyurethane resin ranges from five parts by weight to twenty parts by weight relative to the weight of the magnetic powder.

Please add the following new claims:

9. (New) The magnetic recording medium of claim 1, further wherein the alkali metal sulfonate is incorporated into the resin at concentration of .01 mmol per gram to .4 mmol per gram.
10. (New) The magnetic recording medium of claim 8, further wherein the alkali metal sulfonate is incorporated into the resin at concentration of .01 mmol per gram to .4 mmol per gram.
11. (New) The magnetic recording medium of claim 1, further comprising a quantity of a polar group of a tertiary amine present in a range of .01 mmol/g to .5 mmol/g.
12. (New) The magnetic recording medium of claim 8, further comprising a quantity of a polar group of a tertiary amine present in a range of .01 mmol/g to .5 mmol/g.
13. (New) The magnetic recording medium of claim 9, further comprising a quantity of a polar group of a tertiary amine present in a range of .01 mmol/g to .5 mmol/g.
14. (New) The magnetic recording medium of claim 10, further comprising a quantity of a polar group of a tertiary amine present in a range of .01 mmol/g to .5 mmol/g.